

Océ Specifications



IJM042 Océ Recycled Paper 80 g/m²



Property	Target	Deviation	Unit
Grammage	81	3	g/m ²
Acidity	7,0	1	pH
Thickness	99	3	µm
Whiteness CIE	144	3	
ISO Brightness R457 + UV	103	1	%
ISO Brightness R457 - UV	85	1	%
Opacity	92	1	%
Stiffness (Lorentzen) MD	110	20	mN
Stiffness (Lorentzen) CD	45	5	mN
Porosity	560	150	ml/min
Roughness (Bendtsen) WS	175	50	ml/min
Roughness (Bendtsen) TS	165	50	ml/min

Océ Imaging
Supplies
Product Info

IJM042
Wide-format CAD
Version 1

Storage

Océ CAD Printing Supplies can be stored in virtually all room conditions. However, toner adhesion and line density can be influenced by the relative humidity. It is therefore advisable to repack the supplies in the original wrapping material when not used for a prolonged period.

Océ-Technologies B.V.

P.O. box 101
5900 MA Venlo, the Netherlands
+31 (0) 77 3592222
www.oce.com

Page 1 of 1



Printing for
Professionals

© December 2007 Océ-Technologies B.V. Illustrations and specifications do not necessarily apply to the standard version of machines in all local markets. Technical specifications subject to change without prior notice. All products mentioned in this brochure are claimed as trademarks or registered trademarks of their respective companies.