

Water
Oil
Solvent

Product information

Product Description

This is a premium heavy weight photographic quality paper with a layered microporous coating on a heavy PE coated base.

Physical Properties

Weight	255 g/m ²	L, a*,b* values	95.0, -0.6, -4.5
Thickness	270 µm	Gloss	23 @ 60°
Opacity	> 98.5		

Applications / Features

Indoor display graphics, posters
Photorealistic images
Short term outdoor, if laminated and using pigmented inks

Photorealistic appearance by pearl finishing
Thick, professional photo paper
Quick drying by microporous coating
High Colour intensity
Good lamination properties

Available

Widths (mm)

2" core: 610 914 1067 1270 Refer for our current offering to www.oce.com.

Storage Conditions

Temperature 23°C Relative Humidity 50%
Repack opened rolls when not in use

Print Conditions

Best results are obtained between 15-25°C and 30-65% RH.

Environment, Health & Safety

No Material Safety Data Sheet required. Paper waste suitable for recycling in most countries.
Please refer to local paper recycle station.

Printer

Compatibility

DG Printers	Ink	Rating	Remarks
Océ 5350-300/600	Dye / Pigment	3/1	
Océ CS 5050/5070/5090	Dye / Pigment	3/1	
Encad NJ Pro-E	Dye / Pigment	3/1	
Encad NJ 500/630/700	Dye / Pigment	3/1	
Encad NJ 850	Dye / Pigment	3/1	
Encad 1000i	Dye / Pigment	3/1	
HP 5000/5500	Dye / Pigment	3/3	
Epson 7x00/9x00/10x00	Dye / Pigment	3/3	
Epson 7600/9600/	Ultrachrome	3	
Canon 7200/8200	Dye	3	
Mutoh Falcon	Dye / Pigment	2/3	
Roland Hifi Jet/Pro, Mimaki JV	Dye / Pigment	2/3	
CAD Printers		Rating	
Océ 5150, 5250		3	Setting: other
Océ 5200		3	Minor banding
HP 750C, 500/800, 1050, 4000		3	

3= excellent 2= fair 1= not recommended

Lamination

Compatibility

Hot	Warm	Cold
1	3	3

3= excellent 2= fair 1= not recommended

Hot, heat activated: 105°C -130°C
Warm, heat activated: 85°C - 95°C
Cold, pressure sensitive

Outdoor Use

Outdoor use of this paper without protection is not recommended.

Colour Profiles

Océ develops high-quality colour profiles for media / ink / printer / RIP combinations. Check availability of profiles for your printer on the download section of www.oce.com.



Processing Guidelines



Printing guidelines

Printer and driver settings may need careful setup to ensure optimum performance. Ink loads need to be set appropriately for the ink / printer combination in use.

Lamination guidelines

Dye inks on microporous coated products can exhibit some fading (apart from UV) due to its open structure. Gasses like Ozone cause this phenomenon. Lamination will solve this issue.